

Technical information for tuffbed[®] bedding mortar

SteinTec[®] tuffbed[®] is a high performance, naturally pure hydraulically bonding mortar.

There are no additives or gauging liquids – “just add water” - SteinTec[®] tuffbed[®] is tolerant of a range of water contents, to suit preferred working methods.

SteinTec[®] tuffbed[®] does not require the use of special mixing equipment.

Bedding depths of between 20 mm to 70 mm may be placed in a single layer. Greater depths may be accommodated by placing successive layers of SteinTec[®] tuffbed[®] as a screed bed.

SteinTec[®] tuffbed[®] is shrinkage compensated, reducing the risks of failure associated with building permanent stress into new pavement structures, the inevitable result of excessive shrinkage.

The Elastic Modulus of SteinTec[®] tuffbed[®] is optimised to provide the correct supporting stiffness whilst continually absorbing the thermal and dynamic stresses inherent in all pavement structures.

SteinTec[®] tuffbed[®] complies with or exceeds the performance requirements of BS7533-7 & BS7533-12

Some important performance data for tuffbed[®] bedding mortar:

Lowest working temperature 2°C

Length of working time 2 hours at 20°C - 4 hours at 10°C

Typical compressive strength gain:-

14 days at 20° C ca. 25 N/mm²

28 days at 20° C ca. 35 N/mm²

Flexural strength ca. 4.5 N/mm²

Adhesion strength ca. 1.0 N/mm²

Adhesion strength ca. 2.0 N/mm² (when used with SteinTec[®] tuffbond[®] priming/bonding mortar)

Modulus of Elasticity ca. 14,000 – 18,000 N/mm² according to application and method

Consumption approx. 1.9 kg/litre (2 kg/litre is commonly applied to allow for wastage)

Typical water to add approx. 2.5 litre per 25 kg bag of dry product

It is recommended that sufficient water is added to the bedding mortar to achieve the 150 mm slump recommended in BS7533-4:2006 section 5.4.4.2

SteinTec[®] mortars are resistant to frost and anti-freezing chemicals.

SteinTec[®] tuffbed[®] is supplied as a pre-mixed dry product packed in moisture resistant bags.

Storage life 6 months in dry conditions (mortar can last longer if stored in moisture free conditions, product found to be in a dry powder form is fit for use)

Where an enhanced adhesion bond is required for certain applications, the coating of surfaces using SteinTec[®] tuffbond[®] priming mortar is recommended for use together with SteinTec[®] tuffbed[®]

SteinTec[®]
728 London Road
West Thurrock
Grays, Essex
RM20 3LU

'phone: 01708 860 049

fax: 01708 860 893

Email: info@steintec.co.uk

website: www.steintec.co.uk