

### Technical information for “tuffgrout” jointing mortar

**tuffgrout<sup>®</sup>** is a high performance, naturally pure hydraulically bonding mortar

There are no additives or gauging liquids – “just add water” - **SteinTec<sup>®</sup> tuffgrout<sup>®</sup>** is a highly plastic, free-flowing slurry grout which is straightforward in application and in cleaning of the pavement surface

**tuffgrout<sup>®</sup>** penetrates the most irregular joints and cavities and fills joint widths as small as 3 mm, surplus applied water is displaced naturally and the mortar rapidly densifies before curing commences

**tuffgrout<sup>®</sup>** is shrinkage compensated, reducing the risks of failure associated with building permanent stress into new pavement structures, the inevitable result of excessive shrinkage

The Elastic Modulus of **tuffgrout<sup>®</sup>** is optimised to provide the correct supporting stiffness whilst continually absorbing the thermal and dynamic stresses inherent in all pavement structures

**tuffgrout<sup>®</sup>** complies with or exceeds the performance requirements of BS7533-7 & BS7533-12

#### Some important performance data for tuffgrout<sup>®</sup> jointing mortar:

Lowest working temperature	2°C
Length of working time	60 minutes at 20°C
Typical compressive strength gain:-	
7 days at 20° C	ca. 30 N/mm <sup>2</sup>
28 days at 20° C	ca. 45 N/mm <sup>2</sup>
Bending strength	ca. 7.5 N/mm <sup>2</sup>
Adhesion strength	ca. 1.5 N/mm <sup>2</sup>
Modulus of Elasticity	ca. 24,000
Consumption	approx. 1.8 kg/litre joint space
Typical water to add	5.5 litres per 25 kg bag of dry mortar. Do not add less than 4.5 or more than 5.6 litres water per 25 kg bag of dry mortar

Ensure thorough mixing. Use a forced action mixer or for small quantities a powerful spiral mixing paddle with a speed of approximately 600 rpm, mix thoroughly until a fully homogenous blend is produced

**tuffgrout<sup>®</sup>** is supplied as a pre-mixed dry product packed in moisture resistant bags

Storage life                      6 months in dry conditions (mortar can last longer if stored in moisture free conditions, product found to be in a dry powder form is fit for use)

**SteinTec<sup>®</sup> tuffgrout<sup>®</sup>** jointing mortar is available in 4 standard colours:  
Natural Grey; Mid Grey; Dark Grey and Beige

**SteinTec<sup>®</sup>**  
728 London Road  
West Thurrock  
Grays, Essex  
RM20 3LU

'phone: 01708 860 049

fax: 01708 860 893

Email: [info@steintec.co.uk](mailto:info@steintec.co.uk)

website: [www.steintec.co.uk](http://www.steintec.co.uk)